

## WOOD HANDRAIL DATASHEET

Name: sapele wood handrail

Latin name: Entandrophragma cylindricum

Painting: wood painting, clear coating

Size: 150\*60MM\*2200MM/NOS

Density: 810kgs/m<sup>3</sup> (12% moisture content)

Wood Class: Class AAA best quality

### Other attributes

Painting testing:

Painting finish: Smooth	Test Standard:GB1729	Result: Pass
-------------------------	----------------------	--------------

Adhesive strength: class 2	Test Standard:GB1720	Result: Pass
----------------------------	----------------------	--------------

Flexibility: ≤1mm	Test Standard:GB1731	Result : Pass
-------------------	----------------------	---------------

Pensile hardness: ≥H	Test Standard:GB1728	Result : Pass
----------------------	----------------------	---------------

Painting Drying time:30Min surface, Fully drying in 8 hours with 30 °C

Wood testing:

Wood name: Sapele

Density: Density: 810kgs/m<sup>3</sup> (12% moisture content)

Formaldehyde release: ≤5.0mg/L Test Standard:GB18580-2008 Class E2

Surface: Smooth surface without worm holes

Grade: FIRST-CLASS AAA

Lamination: Solid wood

Moisture ratio: 10% after painting

Adhesive strength: Non.

Useage: for handrail use

more than 300 color such as white, beech, blue and so on

### Packaging and delivery

Packaging Details: wooden case packing

Delivery time: about 15-20days after received TT payment.

Port: Shanghai, China